

Customer No. 20350
TOWNSEND and TOWNSEND and CREW LLP

10/26/00
Atty. Docket No. AM-003984/T03311
TTC Ref.: 6301-033110US
"Express Mail" Label No. 630 576 623 US
Date of Deposit October 18, 2000

BOX PATENT APPLICATION
ASSISTANT COMMISSIONER FOR PATENTS
Washington, D. C. 20231

I hereby certify that this correspondence is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under CFR 1.10 on the date indicated above and is addressed to:

Box Patent Application
Assistance Commissioner for Patents
Washington, D.C. 20231

By Ron Anton
Ron Anton

Sir:

Transmitted herewith for filing under 37 CFR §1.53(b) is the
☒ patent application

Inventor(s)/Applicant Identifier: Timothy Weidman, Michael P. Nault and Josephine J. Chang

For: CAPPING LAYER FOR EXTREME LOW DIELECTRIC CONSTANT FILMS

☒ This application claims priority from each of the following Application Nos./filing dates:
60/160,050, filed October 18, 1999, the disclosure(s) of which is (are) incorporated by reference.

Enclosed are:

☒ 3 sheet(s) of ☐ formal ☒ informal drawing(s); 25 pages of specification including description, claims and abstract; ☒ title page.
☒ A ☐ signed ☒ unsigned Declaration & Power of Attorney.

| | (Col. 1) | (Col. 2) |
|---|-----------|-----------|
| FOR: | NO. FILED | NO. EXTRA |
| BASIC FEE | | |
| TOTAL CLAIMS | 0 | 0 |
| INDEP CLAIMS | 0 | 0 |
| <input type="checkbox"/> MULTIPLE DEPENDENT CLAIM PRESENTED | | |

| SMALL ENTITY | | | NOT SMALL ENTITY | |
|--------------|-----|----|------------------|-----|
| RATE | FEE | OR | RATE | FEE |
| | \$0 | OR | | \$0 |
| x9= | \$0 | OR | x18= | \$0 |
| x39= | \$0 | OR | x78= | \$0 |
| +130= | \$0 | OR | +260= | \$0 |
| TOTAL | \$0 | OR | TOTAL | \$0 |

In view of the unsigned Declaration and Power of Attorney as filed with this application and pursuant to 37 CFR §1.53(f), Applicants request deferral of the filing fee until submission of the Missing Parts of Application.

Respectfully submitted,

TOWNSEND and TOWNSEND and CREW LLP

PLEASE SEND ALL CORRESPONDENCE TO:
PATENT COUNSEL
APPLIED MATERIALS, INC.
P.O. BOX 450A
SANTA CLARA, CA 95052

Telephone: (650) 326-2400
Facsimile: (650) 326-2422

rev. 10/1/00
PA 154649 v1
PA 3103679 v1

Chun-Pok Leung
Reg. No.: 41,405
Attorneys for Applicant

PATENT APPLICATION
Capping Layer for Extreme Low Dielectric Constant Films

Inventor(s):

Timothy Weidman
A Citizen of United States of America, residing at,
776 Henderson Avenue
Sunnyvale, California 94086

Michael P Nault
A Citizen of United States of America, residing at,
1242 Charise Court
San Jose, California 95120

Josephine J. Chang
A Citizen of United States of America, residing at,
6315 Perrin Way
Carmichael, CA 95608

Assignee:

APPLIED MATERIALS, INC.
P.O. Box 450A
Santa Clara, CA 95054

Entity: Large

Capping Layer for Extreme Low Dielectric Constant Films

CROSS-REFERENCES TO RELATED APPLICATIONS

5 This application claims the benefit of U.S. Provisional Application Serial No. 60/160,050, filed October 18, 1999, which is incorporated herein by reference.

BACKGROUND OF THE INVENTION

10 The present invention relates to the formation of dielectric layers. More particularly, embodiments of the present invention relate to a method for capping a low dielectric constant film that is particularly useful as a premetal or intermetal dielectric layer in an integrated circuit.

15 Semiconductor device geometries have dramatically decreased in size since integrated circuits were first introduced several decades ago, and all indications are that this trend will continue. Today's wafer fabrication plants are routinely producing devices having 0.25 μ m and even 0.18 μ m feature sizes, and the plants of the future will soon be producing devices having even smaller geometries.

20 The drive to faster and faster microprocessors, and more powerful microelectronic devices, is dependent on improvements in two chemistry-based areas, optical lithography and low dielectric constant materials. Several semiconductor manufacturers, materials suppliers and research organizations have focused on identifying low and extremely low dielectric constant films. As used herein, low dielectric constant materials are those films having a dielectric constant between 3.0 to 2.5 and extremely low dielectric constant
25 ("ELK") films are those films having a dielectric constant below 2.5 extending to dielectric constants below 2.0.

30 Several candidate low dielectric constant materials are currently under development. Certain specific organic, inorganic and hybrid dielectrics are amongst the current candidates. Additionally, dielectric films from these categories, when made porous, tend to have even lower dielectric constants, and are poised for integration in the next generation of interconnect structures. In terms of deposition techniques, both spin-on and chemical vapor deposition ("CVD") processes are under development, with key challenges remaining around issues of technological performance - i.e. integration.

Among the organic material candidates, organic polymers such as polyarylene and polyarylethers have been most intensively pursued. Two examples of such materials include porous versions of Dow Chemical's SiLK [a spin-on low k material (k between 2.6 - 2.8)] and FLARE from Allied Signal. Spin-on hydrogen silsesquioxane ("HSQ") which has a dielectric constant of 2.9 (k=2.9), is an example of an inorganic dielectric material. Hybrid materials combine organic and inorganic materials. In hybrid materials, cross-linked silicon-oxygen containing polymers designated as polysiloxanes form the basis for conventional spin-on-glass ("SOG") materials. One approach to achieving a lower dielectric constant in hybrid films has been to increase the amount of organic substitution in these materials. For example, where each silicon atom in a spin-on HSQ film is substituted with a methyl group, a methyl-silsesquioxane ("MSQ") results.

As stated above, incorporation of porosity in a dielectric film, regardless of its chemical composition, (i.e. organic, inorganic and hybrid) will reduce the film's dielectric value relative to the solid film. This is due to the fact that the dielectric constant of air is nominally 1. As a result dielectric constants are achievable that are lower than 2.5 including values less than 2.0.

One method of forming a particular type of ELK material which forms a porous oxide film is based on a sol-gel process, in which high porosity films are produced by hydrolysis and polycondensation of a silicon alkoxide such as tetraethylorthosilicate. The sol-gel process is a versatile solution process for making ceramic material. In general, the sol-gel process involves the transition of a system from a homogeneous liquid "sol" (mostly colloidal) into a solid "gel" phase. The starting materials used in the preparation of the "sol" are usually inorganic salts or compounds such as silicon alkoxides. The precursor solutions are typically deposited on a substrate by spin on methods. In a typical sol-gel process, the precursor is subjected to a series of hydrolysis and polymerization reactions to form a colloidal suspension, or a "sol." Further processing of the "sol" enables one to make ceramic materials in different forms. The further processing includes the thermal decomposition of a thermally labile component, which involves the formation of an ordered surfactant-templated mesostructured films by evaporation-induced self-assembly, followed by the thermal decomposition of the template.

In addition to requiring new materials for insulation layers, the trend of decreasing feature size in integrated circuits has created a need for a conductive material having greater conductivity than aluminum which has been the choice in the industry for some time. Many semiconductor manufacturers have turned to copper (Cu) as an

interconnect material in place of aluminum, because copper has a lower resistivity and higher current carrying capacity. However, copper has its own difficulties for IC manufacturing processes. For instance, copper diffuses more readily into surrounding materials and hence requires better materials for a barrier layer than traditionally has been used for aluminum.

5 This greater diffusion characteristic exacerbates the low k porosity described above and places even greater emphasis upon the quality of the barrier layers.

An example of an integrated circuit structure which implements copper as an interconnect material is a dual damascene structure. In a dual damascene structure, the dielectric layer is etched to define both the contacts/vias and the interconnect lines. Metal is inlaid into the defined pattern and any excess metal is removed from the top of the structure in a planarization process, such as chemical mechanical polishing (CMP). Figure 1 shows one example of a dual damascene structure. This structure is appropriate for a first intermetal layer. The integrated circuit 10 includes an underlying substrate 12, which may include a series of layers deposited thereon. The substrate 12 may have transistors therein. A barrier layer 13 may be deposited over the substrate, followed by a dielectric layer 14. The dielectric layer may be undoped silicon dioxide also known as undoped silicon glass (USG), fluorine-doped silicon glass (FSG), or a low k material such as a porous oxide layer or a silicon-carbon or carbon-doped silicon oxide film, or an ELK material. An etch stop layer 16 is deposited over layer 14, pattern etched, and followed by another dielectric layer 18. The structure is then again pattern etched to produce a damascene type pattern. A barrier layer 22 may be needed, which typically has been made from Ta, TaN, Ti, TiN, silicon nitride and plasma enhanced chemical vapor deposited (PECVD) silicon dioxide. However, as explained above, with the smaller feature sizes and increased diffusion propensity of copper, the prior barrier layers are inadequate for optimal performance. Once the conductive material 20 has filled the features, another layer 24, such as a passivation layer, may be deposited. The process described above for a dual damascene structure is exemplary and others may be more appropriate for other particular applications.

Such integration methods when using ELK material and especially porous dielectric materials place additional demands upon the liner or barrier layers. Liner or barrier layers including capping layers such as silicon nitride or silicon dioxide have been deposited adjacent to the low k dielectric layers to prevent the diffusion of byproducts such as moisture and copper. Silicon nitride has been one material of choice for passivation layers. However, silicon nitride has a relatively high dielectric constant (dielectric constant greater than 7.0) and may significantly increase the capacitive coupling between interconnect lines. High

dielectric constants result in a capped insulator layer that does not significantly reduce the overall dielectric constant for the combined insulator-capping layer, which defeats the goals of reducing the dielectric constant of the insulating material. Similarly, problems remain in depositing a silicon dioxide capping layer on a porous film. The capping layer is typically deposited in an oxidative PECVD process. Such an oxidative process damages the surface functionality of the underlying porous film and results in degrading the underlying film's chemical properties, which can degrade the low dielectric constant properties of the film. In addition, although silicon-carbide-type material are known to be appropriate for use as barrier or etch stop layers, their use in IC structures using ELK materials and especially porous ELK materials does not appear to be suitable. This is because the lower k silicon carbide-type materials (such as the commercially available Black Diamond™ [k less than 3.0] developed by Applied Materials of Santa Clara, Ca.) are also typically deposited in an oxidative PECVD process, which as described above could damage the underlying porous film, and the higher k silicon-carbide-type films (such as the commercially available BLOk material™ [k less than 4.5] also developed by Applied Materials of Santa Clara, Ca.) may not be suitable because their k value is too high, which could result in an overall capped ELK film stack having too high of a k value.

Therefore, there is a need for a capping layer that will have the lowest dielectric constant possible and one whose deposition process does not damage the underlying ELK film or degrade the underlying film's chemical properties.

SUMMARY OF THE INVENTION

Embodiments of the present invention provide a silicon-carbide-type or silicon oxycarbide (also often called carbon-doped-oxide [CDO] or organosilicate glass) capping material and method for depositing this capping material on ELK films which are used as a dielectric material in integrated circuits. The ELK film may include any ELK film including but not limited to inorganic, organic and hybrid dielectric materials and their respective porous versions. The capping material may be an amorphous, hydrogenated silicon carbide type material such as the commercially available BLOk™ material, or a carbon-doped oxide material such as the commercially available Black Diamond™ both of which are developed by Applied Materials of Santa Clara, Ca. The amorphous silicon carbide (a-SiC) material is deposited using a plasma process in a non-oxidizing environment and the CDO-type material is deposited using an oxygen-starved plasma process. The CDO material offers the

advantageous property of having a lower dielectric constant value of less than 3.5 as opposed to the a-SiC material which has a dielectric constant of approximately 4.5. The CDO material besides, having a lower dielectric constant also has superior adhesion characteristics with respect to the underlying ELK material. Additionally, the non-oxidative or oxygen-starved plasma processes do not significantly degrade the underlying film's chemical and electrical properties. However, experiments have indicated that despite its higher dielectric constant, the a-SiC-type material (e.g. BLOk™) may be used to generate capped ELK films with similar or even reduced dielectric constants relative to lower k capped films, and may provide composite (i.e. ELK+cap) structures exhibiting superior k stability.

In specific embodiments, the ELK film is capped by a hybrid cap including an amorphous silicon carbide layer deposited on the ELK layer and a carbon-doped oxide layer deposited on the amorphous silicon carbide layer. The amorphous silicon carbide layer may be an amorphous, hydrogenated silicon carbide layer having less than about 5 atomic % oxygen, and more preferably no oxygen, which is deposited from a silicon-containing and carbon-containing precursor in a non-oxidizing environment. The carbon-doped oxide layer may be a carbon-doped silicon oxide layer having about 30-50 atomic % oxygen and about 10-30 atomic % carbon.

These and other embodiments of the present invention, as well its advantages and features, are described in more detail in conjunction with the description below and attached figures.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a simplified cross-sectional view of a portion of an integrated circuit having a dual damascene structure.

Fig. 2 is a flowchart of a process in which a capped ELK layer is formed.

Fig. 3 is a flowchart of a typical process in which a templated sol-gel process is used to deposit a porous silicon oxide layer.

DESCRIPTION OF THE SPECIFIC EMBODIMENTS

Embodiments of this invention provide a method to deposit a silicon carbide type low dielectric constant film as a capping layer or a carbon doped silicon oxide film as a capping layer or a combination thereof over an extremely low dielectric constant ("ELK")

film that may contain oxidizable Si-CH₃ and/or Si-H groups. The capping layer is deposited using a PECVD process in either a non-oxidizing or an oxygen starved plasma. Both the non-oxidizing and the oxygen starved plasma processes prevent or minimize oxidation of the underlying ELK film.

5 The lack of an oxidizing plasma in the PECVD deposition process allows the capping layer to be deposited without degrading the ELK film. Using process conditions described below capping layers having a dielectric constant below 5 and preferably below 3 is deposited on an ELK film. Using these process conditions, the deposition regime of the capping layer does not oxidize the Si-CH₃ or Si-H bonds in the ELK film, and thus allows for
10 a dielectric constant for the combined ELK film and capping layer stack to be less than 3.0. As used herein a capping layer may be a metal diffusion barrier, an etch stop layer, a CMP stop layer, a photoresist barrier or a final passivation layer.

Fig. 2 is a high-level flowchart of a process for forming a capped ELK layer on a substrate according to an embodiment of the present invention. As shown in Fig. 2, first a substrate is placed in a processing chamber (step 200). Next, an ELK material is formed on the substrate (step 210) and finally the ELK layer is capped by a silicon carbide layer, or alternately by a CDO-type layer, or by a combination of a silicon carbide and a CDO layer (step 220). The chamber used to deposit and the one used to cap the film are not the same chamber since the ELK film is a spin-on film and the cap layer is a CVD film. ELK films are
15 porous and are faced with more challenging downstream wafer processing integration issues. As described above, integration issues encompass many wafer processing steps including those described above for a dual damascene process and which may include photoresist deposition, metallization, etch, and CMP. This means that subsequent processes must not damage the underlying ELK film and subsequently deposited films must be isolated from the
20 underlying ELK. Therefore, a capping layer and its method of deposition on an ELK film must not degrade the underlying film's desired properties. Furthermore, the capping layer should preferably possess a low dielectric constant value to ensure that the gains made in depositing an ELK film are not adversely offset by capping it with a high dielectric constant film and effectively increasing the overall dielectric constant for the capped film stack.

30 Before describing the capping layer and a method of depositing the capping material according to embodiments of the present invention, an exemplary ELK material and process for its deposition also in accordance with embodiments of the present invention is described below.

Exemplary ELK Material and Methods For Its Deposition

An exemplary process for forming an ELK layer is based on a sol-gel process. In such a particular sol-gel process for forming a porous low dielectric constant film, surfactants act as the template for the film's porosity. The porous film is generally formed by the deposition on a substrate of a sol-gel precursor followed by selective evaporation of solvent components of the sol-gel precursor to form supramolecular assemblies. The assemblies are then formed into ordered porous films by the pyrolysis of the supramolecular surfactant templates at approximately 400°C.

Figure 3 is a flowchart illustrating a basic sol-gel process that has been previously proposed to deposit ELK films. As shown in Fig. 3, the first step is the synthesis of the stock precursor solution (step 300). The stock precursor solution is prepared, for example, by combining a soluble silicon oxide source, e.g., TEOS (tetraethoxysilane), water, a solvent, e.g. alcohol, and an acid catalyst, e.g. hydrochloric acid, in particular mole ratios at certain prescribed environmental conditions and mixed for certain time periods.

Once the stock solution is obtained, the coating solution is mixed (step 310). The general procedure to prepare the coating solution is to add a surfactant to the stock solution. The surfactants are used as templates for the porous silica. In later processes the surfactants are baked out, leaving behind a porous silicon oxide film. Typical surfactants exhibit an amphiphilic nature, meaning that they can be both hydrophilic and hydrophobic at the same time. Amphiphilic surfactants possess a hydrophilic head group or groups which have a strong affinity for water and a long hydrophobic tail which repels water. The long hydrophobic tail acts as the template member which later provides the pores for the porous film. Amphiphiles can aggregate into supramolecular arrays which have the desired structure to be formed as the template for the porous film. Templating oxides around these arrays leads to materials that exhibit controllable pore sizes and shapes. The surfactants can be anionic, cationic, or nonionic, though for the formation of dielectric layers for IC applications, non-ionic surfactants are generally preferred. The acid catalyst is added to accelerate the condensation reaction of the silica around the supramolecular aggregates.

After the coating solution is mixed it is deposited on the substrate (step 320) using a spinning process where centrifugal draining ensures that the substrate is uniformly coated with the coating solution. The coated substrate is then pre-baked to complete the hydrolysis of the TEOS precursor, continue the gelation process, and drive off any remaining solvent from the film (step 330).

The pre-baked substrate is then further baked to form a hard-baked film (step 340). The temperature range chosen for the bake step will ensure that excess water is evaporated out of the spin cast film. At this stage the film is comprised of a hard-baked matrix of silica and surfactant with the surfactant possessing an interconnected structure characteristic of the type and amount of surfactant employed. The interconnected structure aids the implementation of the subsequent surfactant extraction phase. The interconnected structure provides continuous pathways for the subsequently ablated surfactant molecules to escape from the porous oxide matrix.

Typical silica-based films often have hydrophilic pore walls and aggressively absorb moisture from the surrounding environment. If water, which has a dielectric constant (k) of about 78, is absorbed into the porous film, then the low k dielectric properties of the film can be detrimentally affected. Often these hydrophilic films are annealed at elevated temperatures to remove moisture and to ablate and extract the surfactant out of the silica-surfactant matrix. Such an anneal step leaves behind a porous film exhibiting interconnected pores (step 350). But this is only a temporary solution in a deposition process since the films may still be sensitive to moisture absorption following this procedure.

Some sol-gel processes include further post-deposition treatment steps that are aimed at modifying the surface characteristic of the pores to impart various desired properties, such as hydrophobicity, and increased resistance to certain chemicals. A typical treatment that renders the film more stable is treatment with HMDS (hexamethyldisilazane, $[(CH_3)_3Si-NH-Si-(CH_3)_3]$), in a dehydroxylating process which will remove the hydroxyl groups, replace them with trimethylsilyl groups, and render the film hydrophobic (step 360). Alternatively, or in conjunction with such a silylation step, the porous material may be rendered more hydrophobic by the addition of an alkyl substituted silicon precursor, such as $CH_3Si(OCH_2CH_3)_3$ methyl triethoxysilane or MTES to the precursor formulation.

A variety of alternatives to the above-described sol-gel process for depositing low k materials have been proposed. Many of these alternatives follow the same basic general approach discussed above but vary the choice of ingredients used in the coating solution, the processing times and/or temperatures; combine certain steps; and/or divide other steps into various substeps.

For example, an alternate process for depositing and forming a hardened and stable ELK film according to an embodiment of the present invention is provided below. Using this alternate process, an ELK film was deposited based on a sol-gel-based process as described above by steps 300-350. During steps 300-350 a precursor solution containing at

least a silica precursor composed primarily of a silicon/oxygen compound, water, a solvent, a surfactant and a catalyst was formed. The precursor solution was spun on the wafer and the wafer thermally treated by being baked in a chamber at various temperatures between about 90 °C and 450 °C for between about 30 and 3600 seconds in inert or oxidizing environments having pressures in the range from about 0.1 Torr to atmospheric. The silicon/oxygen compound was selected from the group consisting of tetraethylorthosilicate, tetramethoxysilane, phenyltriethoxy, methyltriethoxysilane and combinations thereof. The solvent was selected from the group consisting of ethanol, isopropanol, propylene glycol monopropyl ether, n-propanol, n-butanol, t-butanol, ethylene glycol and combinations thereof. The surfactant was a non-ionic surfactant selected for example from the group consisting of polyoxyethylene oxides- propylene oxides-polyethylene oxides triblock copolymers, octaethylene glycol monodecyl ether, octaethylene glycol monohexadecyl ether, Triton™ 100, Triton™ 114 and related compounds and combinations thereof. More particularly, the precursor solution used in specific embodiments of this invention has the following composition: tetraethoxysilane (TEOS) - 22.5 gms; methyltriethoxysilane (MTES) - 22.5 gms; propylene glycol monopropyl ether (PGPE) - 100 gms; 0.1N Nitric acid - 24 gms; tetraethylammonium hydroxide (TMAH)(2.4% in water) - 1.0 gms; and Triton X-114 - 9.67 gms (Triton 114 is trademark of a mixture of ethoxylated p-tert-octylphenols manufactured by the Union Carbide Corporation).

As can be recognized, numerous alternate embodiments of the ELK film may be deposited depending upon the choice of the spin-on solution ingredients and processing times and parameters. The ELK film deposited according to the embodiments of this process exhibits the following properties:

- the film is composed essentially of Si-O and Si-CH₃ bonds
- a dielectric constant in the range between 1.6 and 2.3
- a porosity between 20% and 60%
- a modulus of elasticity of between 1.4 and 10 GPa, and generally between 3 and 6 GPa
- a hardness value between 0.4 and 2.0 GPa, and generally between 0.5 and 1.2 GPa
- a refractive index at 633 nm of between 1.1 and 1.5

One apparatus that can be used for the atmospheric deposition of ELK films according to the embodiments of the invention described above is described in commonly assigned and copending U.S. patent application number 09/502,126, entitled A PROCESS

AND AN INTEGRATED TOOL FOR LOW K DIELECTRIC DEPOSITION INCLUDING A PECVD CAPPING MODULE, which is incorporated herein by reference in its entirety.

Having described examples of particular ELK films, materials and methods of capping such films are described below. While it has become apparent that forming ELK films having $k < 2.5$ is feasible, such films which are porous are faced with more challenging downstream wafer processing integration issues, which require unique methods and materials to isolate these ELK films from other layers. As described above, a capping layer and its method of deposition on an ELK film must not degrade the underlying film's desired properties. Furthermore, the capping layer should preferably possess a low dielectric constant value to ensure that the gains made in depositing an ELK film are not adversely offset by capping it with a high dielectric constant film and effectively increasing the overall dielectric constant for the capped film stack.

SiC and CDO Materials As Capping Layers For ELK Films

Embodiments of the present invention provide a silicon-carbide-type or alternately a silicon oxycarbide (also often called carbon-doped-oxide [CDO] or organosilicate glass) capping material, formed according to certain process regimes useful as a capping layer for an integrated circuit, and particularly for an integrated circuit using copper as a conductive material and ELK films as dielectrics. The capping material may be an amorphous, hydrogenated silicon carbide type material such as the commercially available BLOk™ material, or a carbon-doped oxide material such as the commercially available Black Diamond™ both of which are developed by Applied Materials of Santa Clara, Ca. The amorphous silicon carbide (a-SiC) material is deposited using a plasma process in a non-oxidizing environment and the CDO-type material is deposited using an oxygen-starved plasma process. As used herein, an oxygen-starved plasma process is one in which there is sufficient oxygen to react with the precursor to form the CDO-type material, but substantially no excess oxygen is available to react with the substrate. The precursor may be a combination of a silicon-containing precursor and a carbon-containing precursor, an organosilane precursor, or the like.

The CDO material offers the advantageous property of having a lower dielectric constant value of less than 3 as opposed to the a-SiC material which has a dielectric constant of approximately 4.5. The CDO material, besides having a lower dielectric constant, also has superior adhesion characteristics with respect to the underlying ELK material.

Additionally, the non-oxidative or oxygen-starved plasma processes do not significantly degrade the underlying film's chemical and electrical properties because at these oxygen levels the plasma processes do not result in the complete oxidation of the organosilane or the organic component of the underlying ELK film. However, experiments have indicated that despite its higher dielectric constant, the a-SiC-type material (e.g. BLOk™) may be used to generate capped ELK films with similar or even reduced dielectric constants relative to lower k capped films, and may provide composite (i.e. ELK+cap) structures exhibiting superior k stability. The process conditions and experimental results are described below.

As described above, and used herein, a capping layer can be a barrier layer, an etch stop, a CMP stop, or other barrier layers isolating an underlying ELK film from other materials subsequently deposited or etched. Embodiments of the present invention also provide processing regimes that include using a silane-based compound for a silicon source in some embodiments and an organosilane as a silicon and carbon source and potentially in the absence of a substantial amount of oxygen. The process regimes also include the presence of inert gases, such as helium or nitrogen, and at certain temperatures, pressures, power outputs in a PECVD chamber to produce the capping material according to embodiments of the present invention. This particular capping material is especially useful as a capping layer for an ELK film, and may be especially useful in complex structures, such as a damascene structure.

Table 1 below shows some general requirements for a capping layer using copper as a conductive material, although other conductors may be applicable.

| DESIRABLE CHARACTERISTICS OF DIELECTRIC CAPPING LAYER | |
|--|---|
| Good Adhesion | <ul style="list-style-type: none"> • Adhesion to Underlying (ELK Film) and Overlying Layers |
| Not Degrade Underlying Film | <ul style="list-style-type: none"> • Non-oxidizing Deposition Process |
| Good Barrier Property to Copper | <ul style="list-style-type: none"> • No Copper diffusion at 400°-450°C |
| Lower Dielectric Constant | <ul style="list-style-type: none"> • Overall Low Dielectric Constant (K) in IMD Damascene Stack |
| Adjustable (High or Low) Etch Selectivity with respect to ELK Film | <ul style="list-style-type: none"> • Tuned Composition to match or contrast ELK Film to Effect Selectivity |
| Good Electrical Properties | <ul style="list-style-type: none"> • High breakdown Voltage • Low Leakage |

Table 1
Desirable Characteristics of Dielectric Capping Material

Referring to Table 1, adequate adhesion between layers is required to avoid or reduce delamination between them. A measure of adhesion strength is the stud pull test. Using this criterion, an adhesion strength greater than 35 MPa is desired, and tests showed that an adhesion strength of at least 35 MPa was obtained for the capping layer when deposited in accordance with the process described below. The capping material must be such that its deposition process does not degrade the underlying ELK film. This criterion is satisfied by depositing the capping material from a non-oxidizing or oxygen-poor plasma. In case of the oxygen-poor plasma, all or most of the oxygen in the process gas should be consumed in the reaction with the organosilane such that no oxygen is left free to react with the chemical structure of the underlying ELK film. The capping material should also have substantially no diffusion at the substrate annealing temperature of, for example, 400°- 450° C. The term "no substantial" diffusion is intended to be a functional term, such that any actual diffusion into the layer is less than would affect the ability of the capping layer to function as such. For instance, the silicon carbide of an embodiment of the present invention limits the diffusion to about 250Å. The copper diffusion may impair the desired current and voltage paths and contribute to cross-talk. Because of the decreasing feature size, as described above, the lower dielectric constant, preferably less than 5, the lower is the probability for cross talk and RC delay which degrades the overall performance of the device. Related to the low dielectric value of the film is the overall stack dielectric value, which corresponds to the overall dielectric value of the combined capped ELK film (i.e. ELK film and capping layer), where a desirable value should be 3.0 or less.

Because the barrier layer may be used in a damascene structure, it would be beneficial to also have suitable etch stop characteristics, such as an etch selectivity ratio of 1:3 or preferably lower with respect to ELK materials. On the other hand, it may be advantageous to tune the composition of the capping layer to match that of the ELK film to have a low etch selectivity and hence allow for single pass etch of the capping layer and the ELK film. A low etch selectivity may be used in which a via pattern is transferred through the capping layer and into the ELK film at the same time the photoresist is removed. Additionally the capping material should have a high breakdown voltage of 2 MV/cm or more. It should also have a low leakage through the layer, i.e., a low stray direct current that capacitively flows through the material. Another desired characteristic from a commercial standpoint is that the material should be compatible with other processes, so the processes may be conducted in-situ. i.e. in a given chamber, such as in an integrated cluster tool

arrangement, without exposing the material to a contaminating environment, to produce better throughput and process control. This aspect may be particularly important with ELK films, because of their porosity and susceptibility to moisture absorption.

Table 2 below shows the process parameters used in a chamber that allows the film to be used as a capping layer in accordance with specific embodiments of the present invention. In the embodiments tested, the silicon and carbon were derived from a common compound, such as an organosilane-based compound. However, the carbon could be supplemented with other compounds, such as methane. Without limitation, suitable silane-based compounds could include: methylsilane (CH_3SiH_3), dimethylsilane ($(\text{CH}_3)_2\text{SiH}_2$), trimethylsilane ($(\text{CH}_3)_3\text{SiH}$), diethylsilane ($(\text{C}_2\text{H}_5)_2\text{SiH}_2$), propylsilane ($\text{C}_3\text{H}_7\text{SiH}_2$), vinyl methylsilane ($(\text{CH}_2=\text{CH})\text{CH}_2\text{SiH}_2$), 1, 1, 2, 2-tetramethyl disilane ($\text{HSi}(\text{CH}_3)_2\text{-Si}(\text{CH}_3)_2\text{H}$), hexamethyl disilane ($(\text{CH}_3)_3\text{Si-Si}(\text{CH}_3)_3$), 1, 1, 2, 2, 3, 3-hexamethyl trisilane ($\text{H}(\text{CH}_3)_2\text{Si-Si}(\text{CH}_3)_2\text{-SiH}(\text{CH}_3)_2$), 1, 1, 2, 3, 3-pentamethyl trisilane ($\text{H}(\text{CH}_3)_2\text{Si-SiH}(\text{CH}_3)\text{-SiH}(\text{CH}_3)_2$), and other silane related compounds. In addition to organosilanes exemplified by the above list, organosiloxanes such as tetramethyl cyclotetrasiloxane may be used, with or without the addition of another oxygen source, for the deposition of CDO type caps. For the purpose of this invention, the term "organosilane" as used herein includes any silane-based compound having at least one carbon atom attached, including the preceding list, unless otherwise indicated. In Table 2, the compound used was trimethylsilane ("3MS"). A process gas, such as helium, nitrogen, or oxygen was present and might assist in stabilizing the process, although other gases could be used.

| Parameter | Range | CDO | a-SiC | a-SiC + CDO | |
|--------------------------|-----------------------------------|----------|----------|--------------------------|----------|
| | | | | Dep 1: a-SiC; Dep 2: CDO | |
| Silicon and Carbon (3MS) | 50-2400 sccm (6 X oxygen flow) | 600 sccm | 160 sccm | 300 sccm | 600 sccm |
| Oxygen | 0-400 sccm | 100 sccm | 0 | 0 | 100 sccm |
| Helium | 0-5000 sccm | 0 | 400 sccm | 0 | 0 |
| Nitrogen | 0-5000 sccm | 0 | 0 | 0 | 0 |
| RF Power | 100-900 W | 590 W | 560 W | 300 W | 590 W |
| Pressure | 1-15 Torr | 3.8 Torr | 8.7 Torr | 3.8 Torr | 3.8 Torr |
| Temperature | 350° - 450° C | 400 ° C | 400 ° C | 400 ° C | 400 ° C |
| Spacing | 200-600 mil | 280 mil | 280 mil | 280 mil | 280 mil |

Table 2
Process Parameters for Capping Layer Deposition

The inventors have discovered that the process regime described above establishes the suitability of the capping material in meeting the desired criteria of a capping layer for ELK films. As used herein, the capping material includes both the a-SiC and the CDO materials. Using these process regimes, the capping layer can have a low dielectric constant of about 5 or less and can be extended to 3.5 or less by addition of some oxygen. Moreover, the effective dielectric constant of the stack composed of the ELK layer and the cap layer can be less than 2.5 for relatively thin cap layers. This effective dielectric constant meets the needs of a suitable capping layer especially for an ELK and copper-based integrated circuit. The capping material is also suitable as a low k, etch stop material. A low k etch stop material is defined herein as an etch stop material having a dielectric constant equal to or lower than that of silicon nitride (dielectric constant greater than or equal to 7.0) and having a relative oxide to etch selectivity of 2 to 1 or greater. This ratio allows greater control over the etching process and is particularly useful when etching a complex structure, such as a damascene structure. Also by tuning the composition of the capping layer to match that of the ELK film, thus having a low etch selectivity, allows for single pass etch of the capping layer and the ELK film. A low etch selectivity may be used such that a via pattern is transferred through the capping layer and into the ELK film at the same time the photoresist is removed.

To form the capping layer in the preferred process regime, a silicon source such as trimethylsilane may be supplied to a plasma reactor, specifically a reaction zone in a chamber that is typically between the substrate surface and the gas dispersion element, such as a "showerhead," commonly known to those with ordinary skill in the art. Typical commercial PECVD chambers that may be used to practice embodiments of this invention to cap an ELK film, are the DxZ and Producer chambers produced by Applied Materials, Inc. of Santa Clara, California. Alternately, the entire stack (i.e. formation of ELK film and PECVD cap) may be formed in an integrated atmospheric deposition and vacuum cap system as described above. The sequence of operation of a commercial PECVD chamber is well known and needs no explanation for the embodiments of the present invention process regimes.

CDO Cap Deposition

Using such a PECVD chamber, a precursor source such as a trimethylsilane may be provided at a flow rate of about 600 standard cubic centimeters per minute (sccm). The reaction may occur without a substantial source of oxygen introduced into the reaction zone; more particularly a flow of 100 sccm of oxygen gas is used. In conjunction with the

silicon and carbon sources, a process gas, such as helium or nitrogen, may flow into the chamber at a rate of about 0-5000 sccm each respectively. The chamber pressure is maintained between about 1 and 15 Torr, and more particularly 3.8 Torr. An RF power source may apply between about 100 and 900 watts, and preferably about 590 watts to the anode and cathode to form the plasma in the chamber with the silane-based gas. The substrate surface temperature may be maintained between about 300° and 450°C, and more particularly about 400°C during the deposition of the capping layer. The gas may be dispersed at a showerhead to substrate spacing distance between about 200 and 600 mils, and more particularly at 280 mil. Using this recipe a deposition rate of approximately 3700 Å/min was achieved. The measured thickness for the combined capped ELK film was approximately 5270 Å, and the dielectric constant for the capped ELK film was 2.38. The ELK film's dielectric constant was measured to be 2.16. Alternately, an ELK film was capped with a layer of a-SiC material as described below.

a-SiC Cap Deposition

Using such a PECVD chamber, a silicon carbide source such as a trimethylsilane may be delivered at a flow rate of about 160 standard cubic centimeters per minute (sccm). The reaction occurs without any source of oxygen introduced into the reaction zone. In conjunction with the trimethylsilane (silicon and carbon sources), a process gas, such as helium or nitrogen, may flow into the chamber at a rate of about 0-5000 sccm each respectively; more particularly, a flow of 400 sccm of helium is used. The chamber pressure is maintained between about 1 and 15 Torr, and more particularly 3.8 Torr. An RF power source may apply between about 100 and 900 watts, and preferably about 560 watts to the anode and cathode to form the plasma in the chamber with the silane-based gas. The substrate surface temperature may be maintained between about 350° and 450°C, and more particularly about 400°C during the deposition of the capping layer. The gas may be dispersed at a showerhead to substrate spacing distance between about 200 and 600 mils, and more particularly at 280 mil. Using this recipe a deposition rate of approximately 3700 Å/min was achieved. The measured thickness for the combined capped ELK film was approximately 5222 Å, and the dielectric constant for the capped ELK film was 2.22. The ELK film's dielectric constant was measured to be 2.16. Alternately, an ELK film may be capped with a combined capping layer by first depositing an a-SiC cap followed by CDO cap as described below.

Combined a-SiC and CDO Cap Deposition

For the first deposition, namely the a-SiC deposition, a silicon carbide source such as a trimethylsilane may be provided at a flow rate of about 300 standard cubic centimeters per minute (sccm). The reaction occurs without any oxygen introduced into the reaction zone. The chamber pressure is maintained between about 1 and 15 Torr, and more particularly 3.8 Torr. An RF power source may apply between about 100 and 900 watts, and preferably about 300 watts to form the plasma in the chamber with the trimethylsilane. The substrate surface temperature may be maintained between about 350° to 450°C, and more particularly about 400°C during the deposition of the a-SiC capping layer. The gas may be dispersed at a showerhead to substrate spacing distance between about 200 and 600 mils, and more particularly at 280 mil. Next, a CDO cap is deposited on the a-SiC cap. Using the same PECVD chamber, an organosilane such as trimethylsilane at a flow rate of about 600 standard cubic centimeters per minute (sccm) may be used. The carbon may be derived from the trimethylsilane or methylsilane. The reaction may occur without a substantial source of oxygen introduced into the reaction zone; more particularly a flow of 100 sccm of oxygen gas is used. The chamber pressure is maintained between about 1 and 15 Torr, and more particularly 3.8 Torr. An RF power source may apply between about 100 and 900 watts, and preferably about 600 watts to the anode and cathode to form the plasma in the chamber. The substrate surface temperature may be maintained between about 350° and 450°C, and more particularly about 400 °C during the deposition of the capping layer. The gas may be dispersed at a showerhead to substrate spacing distance between about 200 and 600 mils, and more particularly at 280 mil. Using this recipe a deposition rate of approximately 3700 Å/min was achieved. The measured thickness for the combined capped ELK film was approximately 5107 Å, and the dielectric constant for the capped ELK film was 2.15. The ELK film's dielectric constant was measured to be 2.16.

As described above, The capping layer may be a film such as the commercially available BLOk™ material, or a CDO type film compound such as the commercially available Black Diamond™ both of which are developed by Applied Materials of Santa Clara, Ca. The a-SiC compound is deposited using a plasma process in a non-oxidizing environment and the CDO compound is deposited using an oxygen-starved plasma process.

The advantages of such a capping layer for ELK films as compared to traditional capping layers such as silicon oxide and silicon nitride are numerous. The non-

oxidative or alternately the oxygen-starved process regime of embodiments of the present invention does not allow any substantial reaction between the plasma and the Si-C, C-H, and Si-H (if any) bonds present in the underlying ELK film and thus no substantial degradation in the ELK film's desirable dielectric and moisture-repelling properties is observed. Depositing
5 silicon oxide as a capping layer in an oxidizing plasma environment would burn out the carbon in the ELK film, and degrade the ELK film's desirable properties. A set of tests carried out by the inventors, where a 1000 Å SiC capping layer was deposited on a 5000 Å ELK film, showed that overall stack dielectric values of 3.0 or less were achieved, which indicated that the deposition recipe, described below, did not adversely impact the ELK
10 film's properties. The ELK layer alone had a k of 2.0.

Additional tests carried out by the inventors using processes described above, involved the capping of the ELK film with three different capping layers. The first capping layer was the CDO cap; the second was the a-SiC cap, and the third was a two layer cap consisting of first capping the ELK film with an a-SiC cap and then with a CDO layer. The process conditions used for these tests are described above. The results of these experiments were quite unexpected in that the overall dielectric constant of the capped ELK film which was capped with a higher dielectric constant cap was actually lower than the overall dielectric constant of the capped ELK film which was capped with a lower dielectric constant cap.

The CDO material offers the advantageous property of having a lower
20 dielectric constant value of less than 3 as opposed to the a-SiC material which has a dielectric constant of approximately 4.5. Additionally, the oxygen-starved plasma processes do not significantly degrade the underlying film's chemical and electrical properties. However, as stated above, experiments have indicated that despite its higher dielectric constant, the a-SiC-type material (e.g. BLOk™) may be used to generate capped ELK films with similar or even
25 reduced dielectric constants relative to lower k capped films, and may provide composite (i.e. ELK+cap) structures exhibiting superior k stability. These experiments support the unexpected result that films capped with the higher k SiC type film give better overall k values and k stability for the stack than films capped with the lower k SiC material. The inventors believe that this is due to the fact that the lower k cap (CDO) deposition may
30 induce some oxidation of the underlying ELK film during the deposition process. Also because of the oxidation of the ELK film and the lower effectiveness of CDO layers as moisture barriers, the k stability for the ELK-CDO stack is worse than the ELK-a-SiC stack, as shown in Table 3 below.

| Wafer ID | Description | k | k after H2O | % k increase |
|----------|------------------|------|-------------|--------------|
| 356 | Elk | 2.16 | 2.28 | 5.9 |
| 247 | Elk, CDO | 2.38 | 2.47 | 3.6 |
| 244 | Elk, a-Si-C | 2.22 | 2.25 | 1.6 |
| 354 | Elk, a-Sic - CDO | 2.15 | 2.21 | 2.8 |

Table 3
Summary Results of SiC Capped ELK Films

5

The results summarized in Table 3 above are unexpected in that one would anticipate that a film stack consisting of an ELK film and a capping layer would exhibit a lower overall k when capped with a lower k capping layer. It is known that CDO films have a lower k (approximately 3) as compared to a-SiC films (approximately 4.5). However as the results of experiments show, the ELK film capped with the a-SiC exhibits a lower overall k. As shown above, the ELK film stack capped with an a-SiC material has an overall k of 2.22 as compared to the film stack capped with a CDO material which has a k of 2.38. Moreover, the a-Sic capped ELK film exhibits a better k stability. K stability is a measure of the moisture absorption of the film stack. The test is carried out by soaking the film stack in water and then measuring the k of the stack and comparing the post soak k to the non-soaked k. As can be seen from Table 3, the non-capped film experienced a 5.9% increase in its k value due to moisture intake, and of the capped films, the a-SiC capped film only experienced a 1.6% increase in k as compared to the CDO capped film which showed a 3.6% increase in its k value. The inventors having observed the unexpected advantage of capping the ELK film with an a-SiC material, conducted additional tests to determine whether a hybrid cap could be developed. The hybrid cap is one that takes full advantage of the non-oxidizing effect of the a-SiC deposition and the lower k of the CDO films. The last row in Table 3 above shows the results for such a case. The deposition recipe for this case was also described above. The desire to have a hybrid cap is driven by the demands of future ICs to have the lowest k cap but not at the expense of damaging the k value of the underlying ELK films. The inventors believe that an optimum hybrid cap may use an a-SiC cap deposited in a non-oxidizing environment to seal and cap the ELK film, and a CDO film to achieve a lower cap k value. This hybrid cap provides the additional and improved adhesion properties, since CDO films are known to adhere better to layers that may subsequently be deposited on the

20

25

capped ELK film stack. As shown on Table 3, the hybrid cap exhibits an even lower k than the other capped films. The inventors believe that the a-SiC cap may actually be improving the k value of the underlying ELK film by an infiltration-type process. These results suggest that ELK films capped with an a-SiC cap in a non-oxidizing environment are not damaged and are adequately capped by being isolated from other layers.

Other capping materials such as the traditional silicon nitride cap has a relatively high dielectric constant. Although the high dielectric value could be addressed by depositing a relatively thin layer, its deposition can involve the use of an ammonia-based (NH_3) process gas. Such a process gas also reacts with and is detrimental to the underlying ELK film. Lastly and importantly, the adhesion between silicon-carbide type films as taught by the embodiments of the present invention are superior to other PECVD-based films. For example, the SiC material of the present invention has a high adhesion strength with test data showing an adhesion strength of greater than 5 ksi.

Having fully described several embodiments of the method of the present invention for depositing and capping a particular type of ELK film as described above, many other equivalent or alternative methods of depositing and capping ELK layers according to the present invention will be apparent to those skilled in the art. Additionally, the capping layer and the method of depositing the capping layer as described herein are equally applicable and equally advantageous as capping layers for other low dielectric constant or other ELK films. Low dielectric constant or ELK films other than the hybrid carbon doped porous oxide ("CDPO") described above can be other hybrid, organic and inorganic films including the porous variants thereof. Examples of organic films are Dow Chemical's SiLK (a spin-on low k material (k between 2.6 - 2.8)) and FLARE from Allied Signal, and porous versions of these films. Examples of other hybrid films are HSQ and MSQ films and their respective porous variants. These equivalents and alternatives are intended to be included within the scope of the present invention which is set forth in the following claims.

WHAT IS CLAIMED IS:

1 1. A process for capping an extremely low dielectric constant ("ELK")
2 film using a silicon carbide type film comprising:
3 forming an ELK film on a substrate; and
4 depositing an amorphous silicon carbide capping layer on said ELK film.

1 2. The process of claim 1 wherein a combined dielectric constant of a
2 stack consisting of said ELK film and said amorphous silicon carbide capping layer is lower
3 than a combined dielectric constant of another stack consisting of said ELK film and a
4 carbon-doped silicon oxide capping layer which has a dielectric constant less than the
5 dielectric constant of the amorphous silicon carbide capping layer.

1 3. The process of claim 1 wherein said amorphous, hydrogenated silicon
2 carbide capping layer has a dielectric constant of less than approximately 3.5.

1 4. The process of claim 1 wherein said amorphous silicon carbide
2 capping layer is copper diffusion resistant.

1 5. The process of claim 1 wherein said amorphous silicon carbide
2 capping layer does not adversely react with said ELK film to substantially degrade said ELK
3 film's dielectric property.

1 6. The process of claim 1 wherein said amorphous silicon carbide
2 capping layer has an adhesion strength to said ELK film of greater than 35 MPa.

1 7. The process of claim 1 wherein said amorphous silicon carbide
2 capping layer permits no substantial penetration of moisture.

1 8. The process of claim 1 wherein a combined dielectric constant for a
2 stack consisting of said ELK film and said silicon carbide capping layer to be less than 3.0.

1 9. The process of claim 8 wherein the combined dielectric constant is less
2 than 2.5.

1 10. The process of claim 1 wherein said ELK film has a dielectric constant
2 of approximately 3.0 or less.

1 11. The process of claim 10 wherein said ELK film has a dielectric
2 constant of approximately 2.5 or less.

1 12. The process of claim 1 wherein said amorphous silicon carbide
2 capping layer is an amorphous, hydrogenated silicon carbide layer deposited by:
3 introducing a silicon containing precursor, a carbon containing precursor, and
4 a carrier gas into a chamber; and
5 applying energy to react said silicon containing precursor and said carbon
6 containing precursor to deposit said amorphous, hydrogenated silicon carbide capping layer
7 on said ELK film in a non-oxidizing environment.

1 13. The process of claim 12 wherein said silicon containing precursor
2 comprises silane.

1 14. The process of claim 12 wherein said silicon containing precursor and
2 carbon containing precursor are derived from a common organosilane precursor.

1 15. The process of claim 12 wherein said silicon carbide capping layer is
2 deposited at a temperature of between approximately 100° to 450°C.

1 16. The process of claim 12 wherein applying energy comprises generating
2 a plasma in said chamber.

1 17. The process of claim 1 further comprising depositing a carbon-doped
2 oxide layer on said amorphous silicon carbide capping layer.

1 18. The process of claim 17 wherein said carbon-doped oxide layer is a
2 carbon-doped silicon oxide layer formed by:
3 introducing a silicon containing precursor, a carbon containing precursor, and
4 a process gas into a chamber, said process gas including oxygen; and
5 providing a plasma in said chamber to react said silicon containing precursor
6 and said carbon containing precursor in the presence of said plasma to deposit said carbon-
7 doped silicon oxide layer on said amorphous silicon carbide capping layer

1 19. The process of claim 18 wherein said oxygen is introduced at a rate to
2 produce an oxygen-starved plasma for depositing said carbon-doped silicon oxide layer.

1 20. The process of claim 18 wherein said silicon containing precursor and
2 carbon containing precursor are derived from a common organosilane precursor.

1 21. The process of claim 20 wherein said organosilane precursor is
2 provided at a rate approximately six times that of the flow of oxygen gas.

1 22. A process for capping an extremely low dielectric constant ("ELK")
2 film using a silicon carbide material comprising:
3 forming an ELK film on a substrate; and
4 depositing a silicon carbide capping layer having a dielectric constant of
5 approximately less than 5 on said ELK film, where said silicon-carbide layer is produced by a
6 process providing a silicon containing precursor, a carbon containing precursor and process
7 gases comprising oxygen, helium and nitrogen at rates of 0-400 sccm, 0-5000 sccm, and 0-
8 5000 sccm respectively for the process gases, and providing said silicon containing precursor
9 and said carbon containing precursor at a rate approximately six times that of the oxygen and
10 further comprising reacting said silicon and said carbon in a chamber having a pressure in the
11 range of about 1 to 15 Torr with an RF power source supplying a power at approximately
12 300-600 watts and a substrate surface temperature between approximately 100° and
13 approximately 450° C and having a shower head to substrate spacing of approximately 200 to
14 approximately 600 mils, and wherein said capping layer has an adhesion strength of at least
15 about 35 MPa to said ELK film, and wherein the dielectric constant of the for a stack
16 consisting of said ELK film and said silicon carbide layer is at most approximately 3.0.

1 23. A stack having a capped extremely low dielectric constant ("ELK")
2 layer, comprising:
3 a substrate;
4 an ELK layer formed on said substrate;
5 an amorphous silicon carbide layer deposited on said ELK layer; and
6 a carbon-doped oxide layer deposited on said amorphous silicon carbide layer.

1 24. The stack of claim 23 wherein said amorphous silicon carbide layer is
2 an amorphous, hydrogenated silicon carbide layer having less than about 5 atomic % oxygen.

1 25. The stack of claim 24 wherein said amorphous, hydrogenated silicon
2 carbide layer has substantially no oxygen.

1 26. The stack of claim 23 wherein said amorphous silicon carbide layer is
2 deposited from a silicon-containing and carbon-containing precursor in a non-oxidizing
3 environment.

1 27. The stack of claim 23 wherein said carbon-doped oxide layer is a
2 carbon-doped silicon oxide layer.

1 28. The stack of claim 23 wherein said carbon-doped oxide layer
2 comprises about 30-50 atomic % oxygen.

1 29. The stack of claim 23 wherein said carbon-doped oxide layer
2 comprises about 10-30 atomic % carbon.

1 30. The stack of claim 23 wherein said amorphous silicon carbide layer
2 has an effective dielectric constant of approximately less than 5.

1 31. The stack of claim 23 wherein said carbon doped oxide layer has an
2 effective dielectric constant of approximately less than 3.5.

1 32. The stack of claim 23 wherein said stack has a combined dielectric
2 constant of approximately less than 3.

1 33. The stack of claim 32 wherein said stack has a combined dielectric
2 constant of approximately less than 2.5.

1 34. The stack of claim 23 wherein said amorphous silicon carbide layer
2 comprises an etch selectivity ratio of between about 40 to 1 and about 1 to 1.

1 35. The stack of claim 23 wherein said amorphous silicon carbide layer
2 has an adhesion strength to said ELK layer of at least about 35 MPa.

1 36. The stack of claim 23 wherein said amorphous silicon carbide layer is
2 a moisture resistant layer.

1 37. The stack of claim 23 wherein said carbon-doped oxide layer is
2 produced by a process providing a silicon containing precursor, a carbon containing precursor
3 and process gases comprising oxygen, helium and nitrogen at rates of 0-400 sccm, 0-5000
4 sccm, and 0-5000 sccm respectively for the process gases, and providing said silicon

5 containing precursor and said carbon containing precursor at rate approximately six times that
6 of the oxygen and further comprising reacting said silicon and said carbon in a chamber
7 having pressure in the range of about 1 to 15 Torr with an RF power source supplying a
8 power at a rate of approximately 300-600 watts and a substrate surface temperature between
9 approximately 100° and approximately 450° C and having a shower head to substrate spacing
10 of approximately 200 to approximately 600 mils.

1 38. The stack of claim 23 wherein said carbon-doped oxide layer is
2 produced in an oxygen-starved plasma.

3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209

CAPPING LAYER FOR EXTREME LOW DIELECTRIC CONSTANT FILMS**ABSTRACT OF THE DISCLOSURE**

Specific embodiments of the invention provide a silicon-carbide-type or silicon oxycarbide (also often called carbon-doped-oxide [CDO] or organosilicate glass) capping material and method for depositing this capping material on ELK films which are used as a dielectric material in integrated circuits. The ELK film may include any ELK film including but not limited to inorganic, organic and hybrid dielectric materials and their respective porous versions. The silicon-carbide-type material may be an amorphous silicon carbide type material such as the commercially available BLOk™ material, or a carbon-doped oxide material such as the commercially available Black Diamond™ both of which are developed by Applied Materials of Santa Clara, Ca. The amorphous silicon carbide (a-SiC) material is deposited using a plasma process in a non-oxidizing environment and the CDO-type material is deposited using an oxygen-starved plasma process. The non-oxidative or oxygen-starved plasma processes do not significantly degrade the underlying film's chemical and electrical properties. The CDO material offers the advantageous property of having a lower dielectric constant value of less than 3.5 as opposed to the a-SiC material which has a dielectric constant of approximately 4.5. The CDO material besides, having a lower dielectric constant also has a superior adhesion characteristics to the underlying ELK material. However, experiments have indicated that despite its higher dielectric constant, the a-SiC-type material (e.g. BLOk™) may be used to generate capped ELK films with similar or even reduced dielectric constants relative to lower k capped films, and may provide composite (i.e. ELK+cap) structures exhibiting superior k stability.




Fig. 1




Fig. 2




Fig. 3